## **AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions and listings of claims in the application:

1. (Currently Amended) A solid oxide fuel cell having an electrolyte electrode assembly in which a fuel electrode is connected to one face of a first solid electrolyte showing oxide ion conductivity and in which an air electrode is connected to the other face, wherein

the fuel electrode comprises a cermet of a catalyst and of a second solid electrolyte whose oxide ion conductivity is more than <u>or equal to 0.2 S/cm at 1000 °C.</u>

the second solid electrolyte is scandia-stabilized zirconia containing 9 to 12 mol % of scandia (Sc<sub>2</sub>O<sub>3</sub>) to which greater than zero and less than or equal to 2 mol % of at least one kind of oxide selected from ytttria (Y<sub>2</sub>O<sub>3</sub>) and ceria (CeO<sub>2</sub>) is further added, and

the fuel electrode is directly provided with fuel including hydrocarbon and steam.

2-4. (Cancelled).

5. (Currently Amended) The solid oxide fuel cell according to claim [[2]] 1, wherein the second solid electrolyte is further a composite material of the scandia-stabilized zirconia and compounded with less than or equal to 2 wt % of alumina (Al<sub>2</sub>O<sub>3</sub>).

FINNEGAN HENDERSON FARABOW GARRETT & DUNNER LLL

1300 I Street, NW Washington, DC 20005 202.408.4000 Fax 202.408.4400 www.finnegan.com